

## Material Specification: Reflamal S2 / S3 / S4 / S20 / S30

### General Information

#### Appearance

White free-flowing powder

#### Packaging

Paper bags palletized, BigBags or bulk delivery

### Safety Information

This product is non-hazardous, non-toxic and not inflammable. Since legislation may vary from country to country the specific instructions have to be adhered to.

#### REACH reference number

01-2119529246-39-0009

Chemical Properties	Unit	Reflamal S2	Reflamal S3	Reflamal S4	Reflamal S20	Reflamal S30	Method
Al(OH) <sub>3</sub>	%	>99,5	>99,5	>99,5	>99,5	>99,5	Dif.
Na <sub>2</sub> O	%	<0,3	<0,3	<0,3	<0,3	<0,3	XRF
Fe <sub>2</sub> O <sub>3</sub>	%	<0,02	<0,02	<0,02	<0,02	<0,02	XRF
SiO <sub>2</sub>	%	<0,1	<0,1	<0,1	<0,1	<0,1	XRF

  

Physical Properties	Unit	Reflamal S2	Reflamal S3	Reflamal S4	Reflamal S20	Reflamal S30	Method
Loss of ignition (110° - 1,100° C)	%	34,6	34,6	34,6	34,6	34,6	ISO 806
Crystal structure		Gibbsite	Gibbsite	Gibbsite	Gibbsite	Gibbsite	XRD
Specific gravity	g/cm <sup>3</sup>	2,4	2,4	2,4	2,4	2,4	ISO 901
Whiteness, typical		>95	>95	>95	>95	>95	ISO 11664-4 T.4
Bulk density	kg/m <sup>3</sup>	700-900	600-800	500-700	400-600	400-600	ISO 903
Specific surface area (BET)	m <sup>2</sup> /g	1,0-2,3	1,5-3,0	1,8-4,0	5,0-8,0	11,5-15,0	DIN 66132
Medium grain size diameter	µm	13-20	8-14	4,0-7,5	3,5-5,5	1,5-3,5	ISO 13320-1

#### Please note

Information contained herein is intended only for evaluation by technically skilled persons, and is to be used by such persons at their own discretion and risk. Such information is believed to be reliable, but Dadco assumes no responsibility for results obtained or damages resulting from such use.

Typical properties and chemical analyses are intended as examples and are not to be considered as substitutes for actual analyses in those situations where properties and chemical compositions are critical factors. Sales of Dadco products shall be independent and subject exclusively to the terms and conditions set forth in Dadco order acknowledgment.